



5633 Hudson Industrial Parkway
Hudson, OH 44236

p.330-655-0030 f.330-655-0035

www.snsnano.com

NANOSAN® - Sorb

TECHNICAL DATA SHEET

PHYSICAL PROPERTY	TEST	UNITS	RANGE
Mass Per Unit Area	NWSP 130.1.R0(15)	g/m ²	50 – 200
Breaking Force	NWSP 110.4.R0(15)	MPa	1.0 – 2.5
Elongation (Strip)	NWSP 110.4.R0(15)	%	250 - 600
ABSORBENCY (@RT)			
In Saline (0.9% NaCl in water) – 60 sec	NWSP 10.1.R0(15)	%	500 - 1200
In Saline (0.9% NaCl in water) – 30 min	NWSP 240.0.R2(15)	g/g	2.5 – 18.5

- Handling & Storage Conditions – Avoid heat and moisture. Keep material dry and in a sealed container. Material should be stored/processed at temperatures below 60°C/140°F.