



5633 Hudson Industrial Parkway  
Hudson, OH 44236

p.330-655-0030 f.330-655-0035

[www.snsnano.com](http://www.snsnano.com)

# NANOSAN® - Sorb

## TECHNICAL DATA SHEET

PHYSICAL PROPERTY	TEST	UNITS	MINIMUM VALUES
Mass Per Unit Area	WSP 130.1(5)	g/m <sup>2</sup>	50 – 200
Breaking Force	WSP 110.4 (05)	MPa	0.5
Elongation (Strip)	WSP 110.4 (05)	%	250
<b>ABSORBENCY (@RT)</b>			
In Saline (0.9% NaCl in water) – 10 sec	WSP 10.1(05)	%	50
In Saline (0.9% NaCl in water) – 30 min	WSP 240.2(05)	g/g	6.0

- Handling & Storage Conditions – Avoid heat and moisture. Keep material dry and in a sealed container. Material should be stored/processed at temperatures below 60°C/140°F.